

WAKOL Z 626 Levelling Compound

Pre-Technical Information

Area of application

Low-tension, cement-based levelling compound for smoothing out unevenness in layers 2 - 20 mm thick underneath

- Textile flooring
- elastic flooring
- Parquet (minimum 3 mm thickness required)
- cork flooring

indoors.

Special properties



- chromate reduced according to REACH
- suitable for chair castors
- suitable for direct use in conjunction with surface treatment
- can be applied with a rake
- self-levelling
- can be pumped
- suitable for heavy loads from a layer thickness of 3 mm

- 1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions
- 2) Emissions class according to French law
- 3) Cement-based products, low chromate
- 4) Meets the requirements of the European Community
- 5) Suitable for underfloor heating
- 6) Suitable for exposure to castor wheels

Technical data

| | |
|-----------------------------|---|
| Raw material base: | Special cement/quartz mixture with special plastic additives |
| Strength of coating: | up to 20 mm |
| Mixture: | approx. 5,25 – 5,5 l water + 22 kg WAKOL Z 626 |
| Processing time: | approx. 25 minutes |
| Suitable for walking: | after approx. 2 hours |
| Waiting time before laying: | up to 5 mm layer thickness, after 6 hours up to 10 mm layer thickness, after 12 hours up to 20 mm layer thickness, after 24 hours |
| Storage time: | 12 months; store in a cool and dry location, tightly seal any opened bags and use as soon as possible |

Application and consumption⁸⁾

Trowe approx. 1,5 kg/m²/mm layer thickness
l Rake

7) Consumption is dependent on surface structure and absorbability of subfloor.

Subfloors

The subfloor as well as the room climate conditions must meet the requirements of the applicable standards and data sheets. Subfloors must be permanently dry, solid, level, free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

Prime cement paving, calcium sulphate concrete, concrete and other absorbent subfloors with WAKOL D 3004 Primer Concentrate, diluted 1:2 with water, or with WAKOL D 3003 Dispersion Primer. Always comply with primer drying times.

New, well sanded, standardised cast asphalt concrete does not require a primer. Prime used and poorly sanded mastic asphalt concrete as per the relevant standard, and prime old subfloors that have old, waterproof adhesive residues with WAKOL D 3004 Primer Concentrate, diluted with water at a ratio of 1:1, or with WAKOL D 3003 Dispersion Primer.

Usage

Stir WAKOL WAKOL Z 626 Levelling Compound in a clean stirring vessel with approx. 5,25 – 5,5 l clear, cold tap water until free of lumps. The mixing device must not exceed 600 rpm. Leave the compound to stand for approx. 1 minutes before briefly mixing it again.

Apply stirred compound with dripper, smoothing trowel or knife uniformly to the subfloor in the desired layer thickness. Before applying the levelling compound, check whether a sufficiently sized edge strip is available.

Protect the levelling compound layer from direct sunlight and draughts while it sets.

Important

Processing not below floor temperature of +15 ° C and room temperature of +18 ° C, as well as room humidity preferably between 40 % and 65 %, maximum 75 %. All information is based on approx. 20 ° C and 50 % relative air humidity. Warm up all laying materials in due time in heated room.

Observe 3 minimum layer thickness on non-absorbent subfloors e.g. WAKOL PU 280 Polyurethane Primer.

When applying levelling compound in a layer thickness over 5 mm on calcium sulphate- bonded screeds, use only WAKOL PU 280 Polyurethane Primer. Please consult the corresponding data sheet.

The layer thickness permitted on mastic asphalt (IC10 and IC15) is max. 5 mm.

For applying levelling compound on wooden subfloors that are rigidly bolted or glued to the subfloor, only use WAKOL Z 626 Levelling Compound in a maximum of 6 mm.

Do not sand levelling compound before laying parquet in order to ensure the best possible adhesion.

When used as a floor covering, a suitable surface treatment must be applied.

We recommend the use of Loba products that are marked with the Connected Systems for levelling compounds.

Please contact the Application Technology department beforehand for details about the processing of the levelling compound when used as a floor covering.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the currently applicable codes must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at www.wakol.com.

This Technical Information of 05.01.2021 supersedes all previous versions.

506801GB08 0121 WAKOL Z 625 Levelling Compound

Seite 4 von 4

Wakol GmbH
Bottenbacher Straße 30
D-66954
Pirmasens
Tel. +49 6331 8001 131
Fax +49 6331 8001 890
www.wakol.com



Wakol GmbH
Industriestraße 5
A-6841
Mäder
Tel. +43 5523 64 700
Fax +43 5523 64 700 64
www.wakol.at

Wakol Adhesa AG
Schützengasse 28
CH-9410
Heiden
Tel. +41 31 9210 755
Fax +41 31 9212 968
www.wakoladhesa.ch

Wakol Foreco srl
A Via Kennedy 75
I-20010
Marcallo con Casone
Tel. +39 02 9761 939
Fax +39 02 97 253 021
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.
ul. Sławęcińska 16, Macierzysz
PL-05-850
Ożarów Mazowiecki
Tel. +48 22 436 24 20
Fax +48 22 436 24 21
www.loba-wakol.pl

Lecol Chemie B.V.
Schutweg 6
NL-5145 NP
Waalwijk
Tel. +31 416 566 540
Fax +31 416 566 531
www.lecol.nl