

FLOOR PAINT

Colour	Product Code	Pack Size	Box Qty
Grey	FLOORGREY	5LTR	4
Red	FLOORRED	5LTR	4

Product Description

EVERBUILD FLOOR PAINT is a low viscosity, high solids, heavy duty Alkyd based floor paint designed to provide a clean hard wearing finish to concrete, stone and wooden floors subject to light to medium traffic including fork lift trucks, scissor lifts etc. Ideal for use on garage floors, workshops, storerooms, walkways etc. EVERBUILD FLOOR PAINT gives enhanced durability, abrasion resistance and a good resistance to dilute acids/alkalis and oils.

Benefits

- Hard wearing Alkyd formula
- Low viscosity for easy application over large areas
- Can be applied to new/old concrete.

Areas For Use

Concrete, stone and wooden floors in garages, workshops, storerooms, and cloakrooms etc.

Limitations

Ready to use product. Do not dilute. Always follow manufacturer's instructions carefully.

Do not use on concrete floors with a moisture level of above 18%, which do not have a waterproof membrane or concrete floors containing a dust suppressing additive.

New concrete must be a minimum of 6 months old before painting.

Suitable for light traffic only, for areas subject to heavy traffic or constant use, an epoxy-based product is recommended.

Do not use on bitumen or asphalt.

Mechanically or chemically hardened floors may need abrasion prior to application.

As the company cannot be aware of all applications and materials the product can be used on, it is the users responsibility to determine suitability for use. If in doubt contact technical services for advice or request technical data sheet.

Surface Preparation

All surfaces must be clean, dry (to touch) and free grease and other contaminants. Remove all loose and flaking material with a scraper and a stiff brush back to a sound surface. Remove all moss/mould contamination with EVERBUILD MOSS AND MOULD REMOVER. Chemically or mechanically hardened floor may need abrasion prior to use. If in doubt test a small area prior to full application.

Application

Concrete must be a minimum of 6 months old before paint can be applied. Priming is not normally required however if necessary apply a priming coat of 1 part white spirit to 4 parts paint and allow to dry. EVERBUILD FLOOR PAINT is touch dry in 2-3 hours depending on ambient temperatures. NOTE low temperatures can significantly extend drying time. Apply using a brush or roller to give an even coating. 2 coats are normally required allowing 16-24 hours between coats. Clean tools and brushes with white spirits/turps subs after use. Cured product can be removed using xylene.

Specific Data

Colour	Grey / Red
Solids (W/W)	55-60%
M.F.F.T	> 5°C
Film Thickness (dry)	Min 25 – Max 40 microns
Drying Time	Touch dry; 2-3 hours, 16-24 hours between coats.

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store in cool, dry conditions, between 5 and 25°C. PROTECT FROM FROST.

Shelf Life

24 months from date of manufacture.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.